

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problems Mailbox.**

**THIS PAGE BLANK (USPTO)**

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
30 November 2000 (30.11.2000)

PCT

(10) International Publication Number  
**WO 00/72067 A1**

(51) International Patent Classification<sup>7</sup>: **G02B 6/16**

(21) International Application Number: **PCT/GB00/01934**

(22) International Filing Date: **19 May 2000 (19.05.2000)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:  
**9911698.0** **20 May 1999 (20.05.1999)** **GB**

(71) Applicant (for all designated States except US): **UNIVERSITY OF SOUTHAMPTON [GB/GB]; Highfield, Southampton SO17 1BJ (GB).**

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BRODERICK, Neil, Gregory, Raphael [GB/GB]; 98 Harrison Road, Swaythling, Southampton SO17 3TJ (GB). BENNETT, Peter, Jonathan [GB/GB]; 22 Orchard Street, Chelmsford, Essex CM2 0HD (GB). MONRO, Tanya, Mary [GB/GB]; 4 Tower Gardens, Bassett, Southampton SO16**

**7EL (GB). RICHARDSON, David, John [GB/GB]; 1 Midanbury Lane, Bitterne Park, Southampton SO18 4HY (GB).**

(74) Agent: **HAINES, Miles, John; D Young & Co., 21 New Fetter Lane, London EC1A 1DA (GB).**

(81) Designated States (national): **AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.**


(84) Designated States (regional): **ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).**

Published:

— With international search report.

[Continued on next page]

(54) Title: **HOLEY OPTICAL FIBRES**



(57) Abstract: The percentage fraction of fundamental mode power located in the cladding holes of different holey fibres ( $PF_{holes}$ ) is shown as a function of wavelength in microns of the fundamental mode ( $\lambda$ ). Properties of two groups of holey fibres are shown. The upper group of three curves shows embodiments of the invention with  $\Lambda=0.75 \mu m$  and  $d/\Lambda=0.6, 0.7$  &  $0.8$  respectively, where  $d$  is the hole diameter and  $\Lambda$  the hole spacing or pitch. The lower group of curves, which are almost superimposed on each other, show properties of holey fibres representative of the prior art with  $\Lambda=3.2 \mu m$  and  $d/\Lambda=0.6, 0.7$  &  $0.8$  respectively. A huge improvement in the mode power present in the holes is evident. In the prior art curves, the mode power fraction is generally less than 1%, whereas with the illustrated embodiments of the invention, holey fibres with 10-40% of the fundamental mode power in the holes are achieved. Generally the holey fibre should be structured such that the wavelength of the guided light  $\lambda > 2.2\Lambda$ . For telecommunications wavelengths, this means that the hole spacing should be smaller than typical in the prior art, i.e. around  $1 \mu m$  or less, and the hole diameter should be as large as possible in relation to the hole spacing, preferably  $d/\Lambda \geq 0.6$ .



— With amended claims and statement.

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**TITLE OF THE INVENTION**

HOLEY OPTICAL FIBRES

5 **BACKGROUND OF THE INVENTION**

The invention relates to holey fibres and other analogous cavity waveguiding structures.

10 A holey fibre is an optical fibre whose optical confinement mechanism and properties are affected by an array of air holes defined by cavities that run lengthwise down the fibre. Light can be guided within holey fibres by two distinct mechanisms. First, with periodic arrangements of air holes, guidance can be obtained through photonic band gap effects [1]. Second, guidance can be obtained from volume average refractive index effects. This second guidance mechanism does not rely on periodicity  
15 of the air holes [2].

Generally, a holey fibre has a solid core surrounded by a holey cladding region. The structure is fabricated by stacking silica capillaries in a hexagonal close packed array and then removing one of the capillaries and replacing it with a solid silica rod of the same outer dimensions. The fibre stack is then drawn to bundle form in a one or  
20 two stage process. Fabrication of holey fibres is discussed further in the literature [3][4]. In the literature, the core is sometimes referred to as the central index defect, or defect for short, and the surrounding holey cladding as the hole lattice.

Holey fibres are generally characterised in terms of hole size and hole spacing. Because of the fabrication method, the holes are usually periodically spaced, the  
25 period usually being termed as "pitch",  $\Lambda$ , in the literature. Because of the fabrication method, the holes are also usually circular and thus categorised by a diameter,  $d$ . Typical dimensions of existing holey fibres are at least 2 microns for the pitch, although some smaller pitches are mentioned in the literature. Specifically, reference [2] discloses a pitch  $\Lambda=0.925 \mu\text{m}$  with hole diameters of  $d=0.688$  or  $0.833 \mu\text{m}$ .  
30 Moreover, reference [7] discusses a silica core of diameter  $d=0.962 \mu\text{m}$  suspended in air in the context of a theoretical study related to using holey fibre to compensate for group velocity dispersion in standard telecommunications fibre.

-2-

Further general background relating to theories applicable to holey fibres may be found in the literature [5][6].

One application suggested for holey fibres is sensing. It is proposed that a fluid, i.e. gas or liquid, is present in the fibre cavities. A property of the fluid is then  
5 sensed by its effect on that part of the optical mode, generally an evanescent wave part, which propagates in the holey cladding region.

Another application suggested for holey fibres is for low-loss telecommunication fibre. In principal, it might be expected that propagation losses could be reduced in a holey fibre, by virtue of the lower losses associated with the  
10 holes relative to the glass regions of the fibre. More fundamentally, a holey fibre with a photonic band gap could reduce losses through photonic crystal effects.

These applications pre-suppose that a significant proportion of mode power is present in the holey cladding region of the fibre. Holey fibres of the type based on photonic band gap guidance mechanism have very recently been fabricated with a  
15 large percentage of mode power in the "active" holes of the cladding region [14]. However, this type of holey fibre requires periodicity in the hole structure and thus can be expected to be quite difficult to fabricate commercially. Consequently, holey fibres of the type based on the average refractive index guiding mechanism are in principal more attractive since there is no equivalent requirement of hole periodicity. However,  
20 examples of this latter type of holey fibre fabricated to date have only a very small percentage of mode power in the "active" holes of the cladding region. This fact, not hitherto appreciated, has been determined by a theoretical model developed by the inventors, as described in references [8] and [9]. The full contents of references [8] and [9] are incorporated herein by reference.

25 Reference [8] describes a scalar orthogonal function method for holey fibres, which is valid when the holes are small.

Reference [9] extends the model to the vector case, which enables the full range of holey fibres to be modelled. This technique involves decomposing the modal field using localised functions. The central index defect and the hole lattice are  
30 described independently using localised functions for the defect and periodic functions for the holes. This can be efficient and accurate because the quantities are described by functions chosen carefully to suit.

The model of references [8] and [9] allows computation of the proportion of mode power present in the holes of the cladding region of a holey fibre. Using this model, it has been determined that previously fabricated holey fibres guiding by average refractive index effects typically have only around 1% or less of their mode power in the holes.

Clearly, this is not good for any of the proposed holey fibre devices whose efficiency depends on mode power in the holes.

It is therefore an aim of the invention to provide a holey fibre based on average refractive index guidance effects which has a relatively high proportion of mode power in the holes, i.e. a relatively large evanescent overlap of the mode field with the fibre cavities.

## SUMMARY OF THE INVENTION

According to a first aspect of the invention there is provided a holey fibre having holes with a pitch of less than 0.9 microns, more preferably approximately 0.75 microns, positioned adjacent to the core. The pitch is preferably between 0.1 and 0.9 microns, more preferably between 0.5 and 0.9 microns. The ratio of hole size to pitch is preferably greater than or equal to approximately 0.6.

According to a second aspect of the invention there is provided a method of guiding light along an optical fibre by average refractive index effects, the optical fibre having a core and a cladding, the cladding containing holes distributed across the optical fibre to define a pitch, wherein the wavelength of the light is at least approximately 2.2 times the pitch of the holes. The holes preferably have a pitch of less than 0.9 microns, more preferably approximately 0.75 microns. The ratio of hole size to pitch is preferably greater than or equal to approximately 0.6. In an embodiment of the invention, the holes are approximately circular and the ratio of hole diameter to pitch is between 0.6 and 0.8.

With these aspects of the invention it is possible to achieve a massive improvement in the mode power present in the holes without photonic band gap effects. The percentage fraction of fundamental mode power located in the holes is used as a figure of merit. In the prior art holey fibres using average refractive index guidance effects, this is generally less than 1%, often much less. With the invention, it is possible to realise holey fibres based on average refractive index guidance effects that have 10-40% or more of the fundamental mode power in the holes. In some embodiments, the holey fibre may have a highly periodic hole structure and thus may possess significant photonic band gap effects.

The design rules specified above thus allow for large evanescent overlap of the mode field with the air, other fluid or vacuum present in the fibre holes. The holes should be arranged adjacent to the core so that they interact significantly with the optical mode guided by the core. In addition to the small pitch holes arranged around the core, there may be a further group of holes radially outward of the small pitch holes, for example larger holes for ease of fabrication. On the other hand, the small



pitch holes may extend across all the cladding region and constitute the only group of holes in the cladding region.

5 The proposed holey fibres generally incorporate relatively large amounts of air within the structure, typically with a space (air) fill factor in the cladding of greater than 40%. Moreover, the hole spacing, i.e. pitch, should preferably be shorter or comparable to the optical wavelength of the mode of interest.

10 The invention will be of potential interest to all applications requiring an optical interaction with a liquid, gaseous or vacuum field by evanescent field effects. For example, the concentration of pollutants in a gas could be determined by measuring the absorption which occurs as light propagates through the gas for a range of wavelengths [10]. Particular applications of interest are:

- 1) transport of high power optical beams (low optical non-linearity fibre);
- 2) low-loss optical fibre for transmission systems;
- 15 3) optical sensors (gas detection, liquid composition, medical);
- 4) atom optics;
- 5) optical manipulation of microscopic particles;
- 6) particle separation (by mass, induced polarisability, electric dipole moment);
- 7) Raman lasers;
- 20 8) non-linear optical devices;
- 9) referencing of a laser to specific gas absorption lines;
- 10) metrology; and
- 11) dispersion compensation in transmission systems (holey fibre embodying the invention can be made to exhibit high dispersion).

25

**BRIEF DESCRIPTION OF THE DRAWINGS**

For a better understanding of the invention and to show how the same may be carried into effect reference is now made by way of example to the accompanying  
5 drawings in which:

Figure 1 is scanning electron micrograph (SEM) representative of a typical prior art holey fibre with approximate dimensions: hole diameter,  $d=1.9$  microns; and hole spacing,  $\Lambda=3.2$  microns ( $d/\Lambda=0.6$ ); and

10

Figure 2 is a graph showing the percentage fraction of fundamental mode power located in the holes of different holey fibres ( $PF_{\text{holes}}$ ) as a function of wavelength in microns of the fundamental mode ( $\lambda$ ).

## DETAILED DESCRIPTION

To assess the suitability of holey fibres for evanescent field devices, it is crucial to know the magnitude of the overlap of the modal field with the holes. This has not hitherto been addressed. The present invention and its embodiments are based on what is believed to be the first studies of the magnitude of the overlap of the modal field with the holes in holey fibres.

The parameter  $PF_{\text{holes}}$  is defined as the fraction of power of the fundamental mode guided by the holey-fibre waveguiding structure which is located in the holes.

To evaluate  $PF_{\text{holes}}$  the mode profile for a given wavelength is first calculated using the vector model described in reference [9]. It is then straightforward to evaluate  $PF_{\text{holes}}$  at that wavelength numerically. The value of the parameter  $PF_{\text{holes}}$  has been calculated for a range of different holey fibres and wavelengths. The experimental and theoretical results are now discussed with reference to Figure 1 and Figure 2.

Figure 1 is scanning electron micrograph (SEM) representative of a typical prior art holey fibre with approximate dimensions of hole diameter,  $d=1.9 \mu\text{m}$  and hole pitch,  $\Lambda=3.2 \mu\text{m}$  ( $d/\Lambda = 0.6$ ). Holey fibres embodying the invention may have the same general structural features, but have different absolute and/or relative dimensioning as described in the following. In alternative embodiments, the solid core of the holey fibre of Figure 1 may be replaced with a further holey fibre array characterised by smaller feature sizes than the cladding. For example, with a smaller characteristic hole pitch and hole diameter than for the cladding. This general structure is described in reference [13], the contents of which are incorporated herein by reference, specifically in the embodiment of Figure 4 of that document.

Figure 2 is a graph showing the percentage fraction of fundamental mode power located in the holes of different holey fibres ( $PF_{\text{holes}}$ ) as a function of wavelength in microns of the fundamental mode ( $\lambda$ ).

Properties of two groups of holey fibres are shown. The upper group of three curves shows embodiments of the invention with  $\Lambda=0.75 \mu\text{m}$  and  $d/\Lambda=0.6, 0.7$  &  $0.8$  respectively. The lower group of three curves, which are almost superimposed on each

other, show properties of holey fibres representative of the prior art with  $\Lambda=3.2 \mu\text{m}$  and  $d/\Lambda=0.6, 0.7$  &  $0.8$  respectively.

For the fibre of Figure 1, which is representative of the prior art holey fibres,  $\text{PF}_{\text{holes}}$  is surprisingly just  $0.6\%$  at  $\lambda = 1.5 \mu\text{m}$ . More generally, the holey fibres of the prior art typically have a pitch (i.e. hole spacing) in the range  $\Lambda=2-3.5 \mu\text{m}$ . With our theory, it is found that  $\text{PF}_{\text{holes}}$  is insignificant for such holey fibres over the wavelength range  $\lambda = 0.5-2 \mu\text{m}$ . For example, the lower set of curves in Figure 2 corresponds to holey fibres with  $\Lambda=3.2 \mu\text{m}$  and relative hole diameters  $d/\Lambda=0.6, 0.7$  and  $0.8$  respectively.

From the inventors' model of reference [9], it is immediately striking that the field distribution depends strongly on the feature size in the holey fibre relative to wavelength of the guided light. Accordingly,  $\text{PF}_{\text{holes}}$  can be tailored by a suitable choice of holey fibre feature sizes. This does not appear to have been appreciated in the prior art.

To understand how feature size should be chosen, we consider a solid silica rod of diameter  $1.25\Lambda$  suspended in air,  $\Lambda$  being the pitch of an equivalent holey fibre. Although this suspended structure is clearly impractical, it should be a good approximation for large air-fill holey fibres. A value of  $1.25\Lambda$  is chosen because it gives good agreement in the step-index fibre analogy [7]. The modes of this simple structure can be found exactly [11]. It is found that a significant fraction of the fundamental mode is outside the core when  $V < 2$ ,  $V$  being the fibre parameter. This leads to the requirement that  $\lambda$  should be greater than approximately  $2.2\Lambda$  in order for  $\text{PF}_{\text{holes}}$  to be significant. At telecommunications wavelengths, i.e.  $1.3$  and  $1.5 \mu\text{m}$ , this condition is only satisfied for relatively small pitches  $\Lambda$  which leads to very small mode areas of less than approximately  $1 \mu\text{m}^2$ . Consequently, such fibres should also have potential applications in non-linear experiments.

The upper curves in Figure 2 show  $\text{PF}_{\text{holes}}$  for a range of holey fibres with  $\Lambda=0.75 \mu\text{m}$ . The above condition of  $\Lambda$  is greater than or equal to approximately  $2.2\Lambda$  has been used to guide the selection of the pitch  $\Lambda$ . (For the  $1.3 \mu\text{m}$  telecommunication window, this condition is satisfied by a pitch of approximately  $0.6$

$\mu\text{m}$  or less. For the  $1.5 \mu\text{m}$  telecommunications window, the condition is satisfied for a pitch of less than approximately  $0.7 \mu\text{m}$ ).

From Figure 2, it is clear that  $\text{PF}_{\text{holes}}$  is dramatically increased by using the smaller pitch of  $0.75 \mu\text{m}$ . For example,  $\text{PF}_{\text{holes}}$  is approximately 30% at  $1.5 \mu\text{m}$  for a holey fibre with hole separations  $d/\Lambda=0.8$ . So far, we have fabricated holey fibres with  $d/\Lambda$  as large as 0.7 [7]. We thus expect it should be practical to fabricate such fibres. It should not be more difficult to obtain small pitches. The high degree of overlap between the fundamental mode and the holes evident in Figure 2 implies that holey fibres can be fabricated which are useful as evanescent field devices, which cannot be said for typical prior art holey fibre structures as exemplified by the lower curves of Figure 2.

To demonstrate the possibilities for using holey fibres in evanescent field devices, the holey fibre discussed above with  $\Lambda=0.75 \mu\text{m}$  and  $d/\Lambda=0.8$  is now considered. Using  $1.67 \mu\text{m}$  light, it is possible to measure methane concentrations [12]. For this fibre, Figure 2 predicts that  $\text{PF}_{\text{holes}} = 35\%$  at this wavelength. Hence, less than 3 metres of this holey fibre is required to obtain an equivalent free-space path length of 1 metre. Hence by coiling the fibre, extremely long path lengths can be achieved compactly. Another advantage of this geometry is that only tiny gas volumes are required. Three meters of this holey fibre filled using only 30nL of gas would be required. However, it is noted that if the pitch is made too small it becomes difficult to fill the holes with gas in a reasonable time.

Since fibre losses can be low, one could envisage holey fibres with extremely long equivalent free-space path lengths. Also, the combination of the confinement provided by the fibre and the endless single-moded operation which is possible in holey fibre ensures good mode overlap between very different wavelengths over long distances. This is advantageous for sensing, because the absorption signatures of different pollutants can be at quite disparate wavelengths. Hence, holey fibres have the potential to provide an ideal environment for evanescent field devices. Further optimisation of the holey fibre geometry is likely to significantly enhance this potential.

Another type of air-clad fibre was proposed by the article Kaiser et al [6], the full contents of which is incorporated herein by reference. In the Kaiser structure, the core is supported by a thin spoke-like membrane. Such a structure can be single mode. This fibre is closely related to the suspended rod model described above. However, Kaiser et al considered only structures where the membrane thickness 't' is much greater than the wavelength, for which most of the light is located in the glass. By reducing the scale of this structure, which is analogous to reducing the pitch in a holey fibre, the overlap of the mode with the air could be increased. This alternative single-material fibre design could also be used to create compact evanescent field devices. The right is reserved to specifically claim such structures in the present application, or in divisional, continuation or continuation-in-part applications herefrom.

In summary, the overlap of the fundamental optical mode with the air holes in a holey fibre has been studied for what is believed to be the first time. This has been done using a newly developed vector model. It has been shown that a significant fraction of the modal power can be made to overlap with the holes by careful choice of the structural feature sizes using only average refractive index effects, i.e. without resorting to photonic band gap effects.

Furthermore, it has been shown that the structural feature sizes of typical prior art holey fibres based on average refractive index effects have utterly failed to provide any significant mode power in the holes, so that such prior art holey fibres could never have provided efficient evanescent field devices. Most if not all of this type of prior art holey fibres were thus unsuited for evanescent field device applications without this being realised.

The results presented show that holey fibres and analogous structures may indeed become useful for future commercial evanescent field devices. Specifically, the proposed holey fibres should be tolerant to variations in the pitch across the fibre. By contrast, for holey fibre based on guidance by photonic band gap effects, stringent adherence to a constant pitch is required. Thus, although the proposed holey fibre may have a generally periodic hole structure (if only as an artefact of the fabrication process), this is not relied upon for the basic functioning of the device and could be dispensed with. The definitions of the proposed holey fibre in terms of its pitch and

-11-

hole size in the above and in the following claims are thus to be construed as meaning an overall pitch and hole size, possibly with a large variance across the fibre.

**REFERENCES**

1. T A Birks et al: Electronic Letters, vol. 31, pages 1941-1943 (1995)
2. US 5,802,236: DiGiovanni et al: Lucent Technologies Inc.
- 5 3. P J Bennett et al: Optics Letters, vol. 24, pages 1203-1205 (1999)
4. P J Bennett et al: CLEO '99, CWF64, page 293
5. Rosenberg et al: Optics Letters, vol. 21, pages 830-832 (1996).
6. Kaiser & Astle: The Bell System Technical Journal, vol. 53, pages 1021-1039  
(1974)
- 10 7. T A Birks et al: OFC '99, paper FG2, (1999)
8. T M Monro et al: J Lightwave Technology, vol. 17, pages 1093-1102 (1999)
9. T M Monro et al: J Lightwave Technology, vol. 18, pages 50-56 (2000)
10. W Demtroeder: "Laser Spectroscopy" Springer (1996) Section 15.2.1
11. A Snyder & J Love: "Optical Waveguide Theory" Chapman & Hall (1995)  
15 Chapter 14
12. K Ikuta, Y Oki & N J Vasa: CLEO '98, CTHQ4, 1998
13. US 5,155,792: Vali & Chang: Hughes Aircraft Company
14. R F Cregan et al: Science, vol. 285, pages 1537-1539 (1999)



CLAIMS

1. An optical fibre having a core and a cladding, the cladding containing holes distributed across the optical fibre adjacent to the core to define a pitch, wherein the  
5 pitch is less than 0.9 microns.

2. An optical fibre according to claim 1, wherein the pitch is between 0.1 and 0.9 microns.

10 3. An optical fibre according to claim 1, wherein the pitch is between 0.5 and 0.9 microns.

4. An optical fibre according to claim 1, 2 or 3, wherein the holes have a characteristic hole size and the ratio of hole size to pitch is greater than or equal to  
15 approximately 0.6.

5. An optical fibre according to claim 4, wherein the ratio of hole size to pitch is between approximately 0.6 and 0.8.

20 6. An optical fibre according to any one of the preceding claims, wherein the pitch is equal to or less than approximately 0.75, 0.7 or 0.6 microns.

7. An optical fibre according to any one of claims 1 to 6, wherein the core contains holes.  
25

8. An optical fibre according to any one of claims 1 to 6, wherein the core is solid.

9. A method of guiding light along an optical fibre by average refractive index effects, the optical fibre having a core and a cladding, the cladding containing holes  
30 distributed across the optical fibre to define a pitch, wherein the wavelength of the light is at least approximately 2.2 times the pitch of the holes.

10. A method according to claim 9, wherein the pitch is less than 0.9 microns.

11. A method according to claim 9, wherein the pitch is between 0.1 and 0.9  
5 microns.

12. A method according to claim 9, wherein the pitch is between 0.5 and 0.9  
microns.

10 13. A method according to any one of claims 9 to 12, wherein the holes have a  
characteristic hole size and the ratio of hole size to pitch is greater than or equal to  
approximately 0.6.

14. A method according to claim 13, wherein the ratio of hole size to pitch is  
15 between approximately 0.6 and 0.8.

15. A method according to any one of claims 9 to 14, wherein the pitch is equal to  
or less than approximately 0.75, 0.7 or 0.6 microns.

20

**AMENDED CLAIMS**

[received by the International Bureau on 9 October 2000 (09.10.00);  
original claims 1-15 replaced by new claims 1-19 (3 pages)]

1. An optical fibre having a core and a cladding, the cladding containing holes distributed across the optical fibre adjacent to the core to define a pitch, wherein the pitch is less than 0.9 microns, wherein the holes have a characteristic hole size and the ratio of hole size to pitch is greater than or equal to approximately 0.6.

2. An optical fibre according to claim 1, wherein the pitch is between 0.1 and 0.9 microns.

3. An optical fibre according to claim 1, wherein the pitch is between 0.5 and 0.9 microns.

4. An optical fibre according to any one of the preceding claims, wherein the ratio of hole size to pitch is between approximately 0.6 and 0.8.

5. An optical fibre according to any one of the preceding claims, wherein the pitch is equal to or less than approximately 0.75, 0.7 or 0.6 microns.

6. An optical fibre according to any one of claims 1 to 5, wherein the core contains at least one hole.

7. An optical fibre according to any one of claims 1 to 5, wherein the core is solid.

8. An optical fibre according to any one of the preceding claims, wherein the optical fibre has a principal axis of extent and the holes are elongate extending along the principal axis of extent.

9. An optical fibre according to any one of claims 1 to 8, wherein the holes are arranged so that the optical fibre guides by volume average refractive index effects.

10. An optical fibre according to any one of claims 1 to 8, wherein the holes are arranged periodically so that guidance is obtained by photonic band gap effects.

5 11. A method of guiding light along an optical fibre by average refractive index effects, the optical fibre having a core and a cladding, the cladding containing holes distributed across the optical fibre to define a pitch, wherein the wavelength of the light is at least approximately 2.2 times the pitch of the holes, and wherein the holes have a characteristic hole size and the ratio of hole size to pitch is greater than or equal to approximately 0.6.

10

12. A method according to claim 11, wherein the pitch is less than 0.9 microns.

13. A method according to claim 11, wherein the pitch is between 0.1 and 0.9 microns.

15

14. A method according to claim 11, wherein the pitch is between 0.5 and 0.9 microns.

15. A method according to any one of claims 11 to 14, wherein the ratio of hole size to pitch is between approximately 0.6 and 0.8.

20

16. A method according to any one of claims 11 to 15, wherein the pitch is equal to or less than approximately 0.75, 0.7 or 0.6 microns.

25 17. A method according to any one of claims 11 to 16, wherein the optical fibre has a principal axis of extent and the holes are elongate extending along the principal axis of extent.

18. A method according to any one of claims 11 to 17, wherein the holes arranged so that the optical fibre guides by volume average refractive index effects.

30

19. A method according to any one of claims 11 to 17, wherein the holes are arranged periodically so that guidance is obtained by photonic band gap effects.

**STATEMENT UNDER ARTICLE 19 (1)**

The independent claims have been amended to recite the ratio of hole size to pitch, as included in original dependent claims 4 and 13.

The amended claims are considered to be novel over each of WO 00/16141, WO 99/64903 and WO 00/06506

In the cases of WO 99/64903 and WO 00/06506, neither document discloses anything about the ratio of hole size to pitch so novelty is clearly present.

In the case of WO 00/16141, this document discloses a ratio of pore diameter to pitch in the range 0.1 to 0.9 (see page 4, lines 5 to 7). However, WO 00/16141 does not disclose the combination of this ratio with any absolute pitch size. The claimed combination of a pitch of less than 0.9 microns in combination with a specific hole size to pitch ratio in amended claim 1 is thus novel over WO 00/16141. In this respect, it is noted that the statements in WO 00/16141 relating to desired pitch sizes (see page 3) are not linked to the above-mentioned statement relating to the ratio of pore diameter to pitch. This distinction is emphasised by the claims where claim 9 relating to this ratio does not depend on claim 8 in which the pitch range is stated. In summary, claim 1 as amended is novel over WO 00/16141, since the claimed combination of features is not present in any single embodiment of WO 00/16141.

In respect of the amended independent method claim, WO 00/16141 does not disclose any ratio of pore diameter to pitch in combination with the wavelength of light to be guided. Accordingly, the independent method claim as amended is also novel over WO 00/16141. The independent method claim is also novel over WO 00/06506A and WO 99/64903A, since neither of these citations disclose any ratio of hole size to pitch, as already mentioned above.

The amended claims are considered to be novel and inventive over EP 0 779 523 A. It is not understood how the passage referred to in the International search report has any direct bearing on the novelty or inventive step of original claims 4 or 13 which now form the basis of the amended independent claims.

The opportunity has also been taken to add three further dependent claims.

Finally, the present amendments are made without abandonment of subject matter. Specifically, the present amendments have been made to distinguish the claimed subject matter more clearly from WO 00/16141, WO 00/06506 and WO 99/64903 on the basis that these documents are, or will become, citable at least for novelty purposes against the present application. Therefore, in any designated or elected states in which these documents do not ultimately form part of the prior art, we reserve the right to reinstate the original claims.

1/1

Fig. 1





Fig. 2



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 00/01934

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 G02B6/16

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data, INSPEC

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 00 16141 A (CORNING INC ; FAJARDO JAMES C (US); GRANGER GARY P (US)) 23 March 2000 (2000-03-23) page 3, line 1 - page 4, line 7 page 11, line 6 - line 8	1-15
P, X	WO 99 64903 A (BARKOU STIG EIGIL ; BJARKLEV ANDERS OVERGAARD (DK); BROENG JES (DK)) 16 December 1999 (1999-12-16) claims 1, 2, 38, 41, 44, 61, 63	1-15
P, X	WO 00 06506 A (CORNING INC) 10 February 2000 (2000-02-10) page 4, line 16 - line 28 page 7, line 9 - line 23 page 11, line 12 - line 14 page 14, line 17 - line 28; figures 6, 7	1-3, 6-12, 15

-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 August 2000

Date of mailing of the international search report

07/09/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Ciarrocca, M



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 00/01934

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	<p>MONRO T M ET AL: "Developing holey fibres for evanescent field devices"  ELECTRONICS LETTERS, 8 JULY 1999, IEE, UK,  vol. 35, no. 14, pages 1188-1189,  XP002144866  ISSN: 0013-5194  the whole document</p>	1-6,8-15
X	<p>EP 0 779 523 A (MATSUSHITA ELECTRIC WORKS LTD) 18 June 1997 (1997-06-18)  page 4, line 45 - line 56</p>	1,4, 8-10,13
Y	<p>WO 98 44367 A (DEUTSCHE TELEKOM AG ;KOOPS HANS W P (DE); MELTZ GERALD (US); OFT A) 8 October 1998 (1998-10-08)  page 6, paragraph 1; figure 2</p>	1-3
Y	<p>KOOPS H W P: "PHOTONIC CRYSTALS BUILT BY THREE-DIMENSIONAL ADDITIVE LITHOGRAPHY ENABLE INTEGRATED OPTICS OF HIGH DENSITY" PROCEEDINGS OF THE SPIE,US,SPIE, BELLINGHAM, VA, vol. 2849, 5 August 1996 (1996-08-05), pages 248-256, XP000617864  page 249, paragraph 3</p>	1-3
A	<p>US 5 802 236 A (DIGIOVANNI DAVID JOHN ET AL) 1 September 1998 (1998-09-01)  cited in the application  column 5, line 22 - line 52; figure 5</p>	1,9
A	<p>US 5 155 792 A (VALI VICTOR ET AL) 13 October 1992 (1992-10-13)  cited in the application  column 5, line 43 - line 55; figure 4</p>	1,7

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 00/01934

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0016141	A	23-03-2000	AU 5772699 A	03-04-2000
WO 9964903	A	16-12-1999	AU 3026099 A	30-12-1999
			AU 3810699 A	30-12-1999
			WO 9964904 A	16-12-1999
WO 0006506	A	10-02-2000	AU 5002099 A	21-02-2000
EP 0779523	A	18-06-1997	JP 2998619 B	11-01-2000
			JP 9156958 A	17-06-1997
			JP 2867945 B	10-03-1999
			JP 9230157 A	05-09-1997
			US 5790742 A	04-08-1998
WO 9844367	A	08-10-1998	AU 8008198 A	22-10-1998
			EP 0970396 A	12-01-2000
			US 6075915 A	13-06-2000
US 5802236	A	01-09-1998	EP 0810453 A	03-12-1997
			JP 10095628 A	14-04-1998
US 5155792	A	13-10-1992	EP 0520653 A	30-12-1992
			JP 5264828 A	15-10-1993